

WORKWEAR FABRIC INFORMATION



FABRIC	Indestructible
FINISH	Crease Resist
PRODUCT CODE	0177 80

FABRIC DESCRIPTION / CHARACTERISTICS	
BLEND (FIBRE CONTENT)	Polyester 65 %, Cotton 35 %
FINISHED WEIGHT	245 g/m ²
YARN COUNT	warp Nm 26 weft Nm 24
FINISHED CONSTRUCTION	warp 34 threads/cm weft 22 threads/cm
WEAVE	2x1 Z Twill
MINIMUM USABLE WIDTH	150 cm

PHYSICAL PERFORMANCE		PRE-TREATMENT	TEST METHOD	RESULTS	ETSA RATING	
TENSILE STRENGTH	warp			ISO 13934-1	1200 N	●●●
	weft				650 N	
PILLING	Martindale	5.000 Rev.	5x ISO 15797	ISO 12945-2	3/4	●●●
SHRINKAGE IN WASHING			5x @75°C	ISO 15797	± 2,0 %	●●●
Wash & Wear / Crease Recovery			3x ISO 15797	ISO 15487	3/4	●●●

COLOUR PERFORMANCE		TEST METHOD	RESULTS	ETSA RATING	
RUBBING DRY		ISO 105 x 12	4	N/A*	
WASHING	colour change		ISO 105 C06 E1S	4	N/A*
	colour staining	PES	ISO 105 C06 E1S	3/4	N/A*
	colour staining	COTTON	ISO 105 C06 E1S	3/4	N/A*
DRY CLEANING	colour change		ISO 105 D 01	4	N/A*
PERSPIRATION	colour change		ISO 105 E 04	4	N/A*
	colour staining	PES	ISO 105 E 04	3/4	N/A*
	colour staining	COTTON	ISO 105 E 04	3/4	N/A*
LIGHT FASTNESS			ISO 105 B 02	5	N/A*
NOTES	Colour performance results shown are average values. Dark and special colours may not meet figures quoted.				

OTHER PERFORMANCE		TEST METHOD	RESULT

NOTES	SPECIAL FEATURES
<p>Characteristics may vary within commercial tolerances.</p> <p>PRODUCT CARE – ALL FABRICS ARE ALSO TESTED TO KLOPMAN TEST METHODS</p>	

CARE LABELLING	
<p>DOMESTIC WASH</p> <p>WHITE ONLY</p>	<p>INDUSTRIAL LAUNDERING</p> <p>SEE KLOPMAN LAUNDERING RECOMMENDATION</p>

DATE 28/11/2012

www.klopman.com



This document is for information only. For a controlled document please contact our technical service.
N/A* Not available for this product.